

nyloprint® WS nyloprint® WS Digital

Water washable, steel based letterpress printing plates for brilliant print quality

Product features

Wide range of applications

- Ideal for laminated tubes, cups and cans printing, continous business forms, security printing, label printing, female die for blind embossing
- Suitable for rotary letterpress, imprinting units and special-purpose printing presses

Highest print quality

- High print contrast with an exceptional tonal range
- Brilliant halftone gradations due to very fine halftone dots (< 20 micron)
- Smooth vignettes
- High resolution up to 10 160 dpi
- Excellent solid density due to brilliant ink transfer
- Very good durability for long print runs
- Reliably reusable for repeat orders

Efficient, reliable and fast plate processing

- Wide exposure latitude combined with high intermediate depths
- Highly productive and cost saving due to plate processing within 25-35 min
- Reduced down times on press due to fast replacement of damaged plates

Excellent mounting properties of nyloprint® WS-T

 nyloprint® WS-T and nyloprint® WS-T Digital with excellent adaptation to different cylinders diameters due to very high flexibility of the thin steel base

Advantages of nyloprint® Digital

Higher print quality

- Reproduction of finer details and less dot gain due to digital imaging
- High dimensional stability
- No defects caused by dust and damaged films
- No data loss during transfer
- Smoother plate surface can achieve higher density
- Highly consistent especially when repeating plate processing

Cost effective and environmentally friendly

- No film costs
- No chemicals for film development
- Electronic filing of graphics, film storage is redundant
- Easy and fast data exchange worldwide



nyloprint® WS | nyloprint® WS Digital

	nyloprint® WS nyloprint® WS Digital					nyloprint® WS-T nyloprint® WS-T Digital¹
	43	58	73	83	94	73
Technical characteristics						
Base material			steel			thin steel
Colour of raw plate			red			red
Total thickness ² (mm) (inch)	0.43 (0.017")	0.58 (0.023")	0.73 (0.029")	0.83 (0.033")	0.94 (0.037")	0.73 (0.029")
Plate hardness (Shore D)	89	84	77	76	73	77
Relief depth (mm) (inch)	0.20 (0.008")	0.32 (0.013")	0.46 (0.018")	0.56 (0.022")	0.67 (0.026")	0.56 (0.022")
Tonal range (%) nyloprint® WS at screen ruling nyloprint® WS Digital	2 – 95 at 60 l/cm (150 lpi) 1 – 98 at 60 l/cm (150 lpi)					2-95 at 60 l/cm (150 lpi) 1-98 at 60 l/cm (150 lpi)
Fine line width (down to µm)	100	100	100	100	100	100
Isolated dot diameter (down to µm)	200	200	200	200	200	200
Distortion factor (mm) (inch)	2.08 (0.082")	3.02 (0. 11 9")	3.85 (0. 1 52")	4.49 (0. 177 ")	5.19 (0.204")	4.34 (0.171")

Processing parameters ³						
Main exposure (min) nyloprint® WS nyloprint® WS Digital	1.0-5.0 1.0-3.5 (without vacuum film)	3.0 – 5.0 1.5 – 3.5 (without vacuum film)				
Washout at 30 °C / 86 °F (min)	1.0 - 3.5	2.5 - 3.5				
Drying time at 80°C / 176°F (min)	15	10-15				
Post exposure (min)	2	2				

¹ non-standard product

Suitable equipment nyloprint® WS plates can be processed with nyloprint® processing equipment and all similar devices.

nyloprint® WS Digital plates can be used with all laser systems suitable for imaging letterpress

plates.

Printing inks and varnishes Suitable for UV and oil based inks and varnishes.

Washout medium For washout only tap water is needed.

Processing information A detailed description of the individual platemaking steps, as well as detailed information about

processing and storing can be found in the nyloprint® User Guide.

High quality standard nyloprint® printing plates are manufactured according to DIN ISO 9001 and DIN ISO 14001

standards and requirements. This process guarantees our customers consistent high quality

products and services.

You are welcome to contact us for further information.

Flint Group Flexographic Products Sieglestrasse 25 70469 Stuttgart Germany T +49 711 9816-541 F +49 711 9816-801 info.flexo@flintgrp.com www.flintgrp.com

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of Flint Group's knowledge. No liability for any errors, facts or opinions is accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted. Product names followed by ® are trademarks registered by Flint Group (represented by Flint Group US LLC or Flint Group Germany GmbH)



standard thicknesses currently available – subject to change

³ All processing parameters depend on, among others, the processing equipment and lamp age. The above mentioned processing parameters were established under optimum conditions on nyloprint® processing equipment. Under other conditions the processing times can differ from these. Therefore the above mentioned values are only to be used as a guide.